

**OKLAHOMA DEPARTMENT OF TRANSPORTATION  
SPECIAL PROVISION  
FOR  
WARM MIX ASPHALT**

This special provision amends and where in conflict, supersedes applicable sections of the 2009 Standard Specifications for Highway Construction, English and Metric. The units for this project are those specified in the project plans.

*(Add the following:)*

**411.01 DESCRIPTION**

Warm Mix Asphalt (WMA) is defined as an asphalt binder and aggregate mixture which, by additive or process, can be produced and placed at a reduced temperature from normal HMA temperatures. WMA requirements are the same as for HMA except where noted.

**411.04 CONSTRUCTION METHODS**

**K. Compaction**

**(1) General**

Ensure that the WMA immediately behind the paver is at least 215°F [102°C].